

COLOUR FASTNESS VALUES - ISO Standard

COLOUR	CHLORINATE D WATER ISO 105-E03	LIGHT ISO 105-B02	WATER ISO 105-E01				SEA WATER ISO 105-E02				WASHING 40°C ISO 105-C06 A2S				CROCKING ISO 105-X12		ACID PERSPIRATION PH 5.5 ISO 105-E04			
	C.C.	C.C.	C.C.	CO	PA	PL	C.C.	CO	PA	PL	C.C.	CO	PA	PL	S.CO DRY	S.CO WET	C.C.	CO	PA	
	50 mg/l																			
0710 Solid White	3-4	4	5	5	5	5	5	5	5	5	4-5	4-5	4-5	4-5	5	5	5	5	5	5
3516 Azure	3-4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
4316 Cyan	4	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
4016	3	3-4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
4116	3	3-4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
4216	3-4	3-4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
2717 Sea Green	4	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4	4-5	4-5	4-5	4-5	4-5	4-5
Fluorescent Colours - CF to Light AATCC 16-10 AFU'																				
1011 Acid Yellow	3-4	3-4	4-5	4-5	4	4-5	4-5	4-5	4	4-5	4-5	4	2-3	3-4	4-5	4	4-5	4-5	4	4
2012 Paw Paw	3-4	3-4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	3-4	4	4-5	4	4-5	4-5	4-5	4-5
1912 Acid Orange	4	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	3	3-4	4-5	4-5	4-5	4-5	4-5	4-5
2112	4	3-4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	3-4	4	4-5	4-5	4-5	4-5	4-5	4-5
2213 Pink Splash	3-4	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	3-4	4	4-5	4-5	4-5	4-5	4-5	4-5
2313 Acid Pink	3-4	3-4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5
2413 Hot Pink	3-4	3	4-5	4-5	4	4-5	4-5	4-5	4	4-5	4-5	4	3-4	4	4-5	4-5	4-5	4-5	4-5	4
2513	4	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	3-4	4	4-5	4-5	4-5	4-5	4-5	4-5
1114 Tang	3-4	2-3	4-5	4-5	4	4-5	4-5	4-5	4	4-5	4-5	4	3-4	4	4-5	4-5	4-5	4-5	4-5	4
2617 Acid Green	3-4	3	4-5	4-5	4	4-5	4-5	4-5	4	4-5	4-5	4	3	3-4	4-5	4	4-5	4-5	4-5	4